



Technical Datasheet AMBARINO® High-Class

Physical properties:	Measured data:
Vickers hardness	700 MPa [#]
Modulus of elasticity	9900 MPa [#]
Flexural strength	175 MPa [#]
Compressive strength	490 MPa [#]
Colourstability	meets ISO 4049
Absorption of water	15.66µg/mm ^{3#}
Water solubility	0.04 µg/mm ^{3#}
Density	1.890 g/cm ³
Filler content	70,5 % (weigth)
Radiopacity	2.4 ATE meets ISO 4049

= measured data ± 10%

Marburg, 20.10.2015

creamed GmbH & Co.
Produktions- und Handels KG
Industriestraße 4a
D-35041 Marburg
Tel.: 06421/16 89 93-0
Fax: 06421/16 89 93-1

Geschäftsführer:
Robert H. Lemmer
Amtsgericht Marburg
HRA 4470
www.creamed.de
creamed@t-online.de

Raiffeisenbank eG Ebsdorfergrund
Konto Nr. 508748 / BLZ 533 617 24
IBAN DE40 5336 1724 0000 5087 48
BIC GENODEF1EBG
StNr: 031 310 30113
Ust-IdNr.: DE270729624

creamed Verwaltungs-
und Beteiligungs GmbH
Industriestraße 4a
D-35041 Marburg
Amtsgericht Marburg
HRB 5689